

INDUSTRIAL AND
ARCHITECTURAL

PRODUCTS GUIDE

FROM MARTIN-SENOUR



MARTIN
SENOUR
PAINTS®

Where paint becomes design.™

For more information call
1-800-MSP-5270

INTERIOR PLASTER, GYPSUM, KEENE'S CEMENT

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:			
										To Touch	To Recoat		
Walls & Ceilings	Alkyd	Flat	ProLine Premium Alkyd Flat Wall Paint**	T.P.S. Multi-Surface Latex	0-10@85°	400	2.0	49	74	2-5 Hrs.	24 Hrs.		
			Platinum Latex Flat Wall Paint**	Enamel Undercoater or	0-5@85°	400	1.6	40	56	1 Hr.	4 Hrs.		
	Latex	Flat	Bright Life Latex Flat Wall Paint**	T.P.S. Alkyd Enamel Undercoater	0-5@85°	400	1.6	41	58	1 Hr.	4 Hrs.		
			ProLine Supreme Low Odor Latex Flat Wall Paint**	(same)	0-5@85°	400	1.7	42	60	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Flat Wall Paint**	(same)	0-2@85°	400	1.4	34	53	1 Hr.	4 Hrs.		
			ProLine Premium Latex Flat Wall Paint**	(same)	0-5@85°	400	1.3	32	50	1 Hr.	4 Hrs.		
			Latex Ceiling Paint "Best"***	(same)	0-5@85°	400	1.2	31	50	1 Hr.	4 Hrs.		
			Latex Ceiling Paint "Better"***	(same)	0-5@85°	400	1.1	28	46	1 Hr.	4 Hrs.		
			Alkyd	Eggshell	ProLine Premium Alkyd Eggshell Enamel**	(same)	20-30@60°	400	1.8	44	65	2-5 Hrs.	24 Hrs.
					Platinum Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	40	55	1 Hr.	4 Hrs.
	Latex	Eggshell	Bright Life Latex Eggshell Enamel**	(same)	10-20@85°	400	1.3	33	47	1 Hr.	4 Hrs.		
			ProLine Supreme Low Odor Latex Eggshell Enamel**	(same)	10-20@85°	400	1.6	39	53	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	39	52	1 Hr.	4 Hrs.		
			ProLine Premium Latex Eggshell Enamel**	(same)	15-20@85°	400	1.2	30	44	1 Hr.	4 Hrs.		
			Alkyd	Semi-Gloss	Platinum Alkyd Satin Gloss Enamel**	(same)	25-35@60°	350-400	1.7	43	63	4-6 Hrs.	24 Hrs.
					Bright Life Alkyd Satin Gloss Enamel**	(same)	55-65@60°	400	1.7	43	63	2-4 Hrs.	24 Hrs.
	Latex	Semi-Gloss	ProLine Premium Alkyd Semi-Gloss Enamel**	(same)	55-65@60°	400	1.6	40	60	2-5 Hrs.	24 Hrs.		
			Platinum Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.6	39	52	1 Hr.	4 Hrs.		
			Kitchen, Bath & Trim Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	200-300	3	38	50	1 Hr.	4 Hrs.		
			Bright Life Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.		
			ProLine Supreme Low Odor Latex Semi-Gloss Enamel**	(same)	35-45@60°	400	1.6	40	48	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Semi-Gloss Enamel**	(same)	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.		
			ProLine Premium Latex Semi-Gloss Enamel**	(same)	25-35@60°	400	1.2	30	38	1 Hr.	4 Hrs.		
			Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.		
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	1.5	38	50	1 Hr.	4 Hrs.		
			Alkyd	Gloss	Bright Life Alkyd Gloss Enamel**	(same)	80+@60°	400	1.6	39	56	2-4 Hrs.	24 Hrs.
	Tough Coat Heavy Duty Alkyd High Gloss Enamel**	(same)			70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.		
	Latex	Gloss	Bright Life Latex High Gloss Enamel**	(same)	60-80@60°	400	1.5	38	48	1 Hr.	4 Hrs.		
			Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.		
	Alkyd	Flat	ProLine Premium Alkyd Dry Fall Flat**	(same)	0-8@85°	295	3.3	55	80	10 Min.	2-6 Hrs.		
	Latex	Flat	ProLine Premium Latex Dry Fall Flat**	(same)	0-10@85°	225	3.0	42	60	30 Min.	1 Hr.		
	Alkyd	Semi-Gloss	ProLine Premium Alkyd Dry Fall Semi-Gloss**	(same)	18-28@60°	260	2.9	49	71	10 Min.	2-6 Hrs.		
	Latex	Semi-Gloss	ProLine Premium Latex Dry Fall Semi-Gloss**	(same)	15-25@60°	225	3.0	41	54	30 Min.	1 Hr.		
	Epoxy	Semi-Gloss	Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	T.P.S. Multi-Surface Latex	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs., <30 Days		
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	Enamel Undercoater	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
	Epoxy	Gloss	Tough Coat Polyamide Catalyzed Epoxy Gloss**	(same)	80+@60°	185	4	56	70	1 Hr.	>6 Hrs., <30 Days		
			Tough Coat Modified Epoxy High Gloss Enamel**	(same)	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.		
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		

INTERIOR DRYWALL

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:			
										To Touch	To Recoat		
Walls & Ceilings, Gypsum Board, Wood Pulp Board, Etc.	Alkyd	Flat	ProLine Premium Alkyd Flat Wall Paint**	T.P.S. Multi-Surface Latex	0-10@85°	400	2.0	49	74	2-5 Hrs.	24 Hrs.		
			Platinum Latex Flat Wall Paint**	Enamel Undercoater or	0-5@85°	400	1.6	40	56	1 Hr.	4 Hrs.		
	Latex	Flat	Bright Life Latex Flat Wall Paint**	T.P.S. Latex Wall Primer	0-5@85°	400	1.6	41	58	1 Hr.	4 Hrs.		
			ProLine Supreme Low Odor Latex Flat Wall Paint**	(same)	0-5@85°	400	1.7	42	60	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Flat Wall Paint**	(same)	0-2@85°	400	1.4	34	53	1 Hr.	4 Hrs.		
			ProLine Premium Latex Flat Wall Paint**	(same)	0-5@85°	400	1.3	32	50	1 Hr.	4 Hrs.		
			Latex Ceiling Paint "Best"***	(same)	0-5@85°	400	1.2	31	50	1 Hr.	4 Hrs.		
			Latex Ceiling Paint "Better"***	(same)	0-5@85°	400	1.1	28	46	1 Hr.	4 Hrs.		
			Alkyd	Eggshell	ProLine Premium Alkyd Eggshell Enamel**	(same)	20-30@60°	400	1.8	44	65	2-5 Hrs.	24 Hrs.
					Platinum Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	40	55	1 Hr.	4 Hrs.
	Latex	Eggshell	Bright Life Latex Eggshell Enamel**	(same)	10-20@85°	400	1.3	33	47	1 Hr.	4 Hrs.		
			ProLine Supreme Low Odor Latex Eggshell Enamel**	(same)	10-20@85°	400	1.6	39	53	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	39	52	1 Hr.	4 Hrs.		
			ProLine Premium Latex Eggshell Enamel**	(same)	15-20@85°	400	1.2	30	44	1 Hr.	4 Hrs.		
			Alkyd	Semi-Gloss	Platinum Alkyd Satin Gloss Enamel**	(same)	25-35@60°	350-400	2.3	54	72	2-4 Hrs.	24 Hrs.
					Bright Life Alkyd Satin Gloss Enamel**	(same)	55-65@60°	400	1.7	43	63	2-4 Hrs.	24 Hrs.
	Latex	Semi-Gloss	ProLine Premium Alkyd Semi-Gloss Enamel**	(same)	55-65@60°	400	1.6	40	60	2-5 Hrs.	24 Hrs.		
			Platinum Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.6	39	52	1 Hr.	4 Hrs.		
			Kitchen, Bath & Trim Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	200-300	3	38	50	1 Hr.	4 Hrs.		
			Bright Life Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.		
			ProLine Supreme Low Odor Latex Semi-Gloss Enamel**	(same)	35-45@60°	400	1.6	40	48	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Semi-Gloss Enamel**	(same)	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.		
			ProLine Premium Latex Semi-Gloss Enamel**	(same)	25-35@60°	400	1.2	30	38	1 Hr.	4 Hrs.		
			Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.		
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	1.5	38	50	1 Hr.	4 Hrs.		
			Alkyd	Gloss	Bright Life Alkyd Gloss Enamel**	(same)	80+@60°	400	1.6	39	56	2-4 Hrs.	24 Hrs.
	Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	(same)			70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.		
	Latex	Gloss	Bright Life Latex High Gloss Enamel**	(same)	60-80@60°	400	1.5	38	48	1 Hr.	4 Hrs.		
			Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.		
	Alkyd	Flat	ProLine Premium Alkyd Dry Fall Flat**	(same)	0-8@85°	295	3.3	55	80	10 Min.	2-6 Hrs.		
	Latex	Flat	ProLine Premium Latex Dry Fall Flat**	None	0-10@85°	225	3.0	42	60	30 Min.	1 Hr.		
	Alkyd	Semi-Gloss	ProLine Premium Alkyd Dry Fall Semi-Gloss**	(same)	18-28@60°	260	2.9	49	71	10 Min.	2-6 Hrs.		
	Latex	Semi-Gloss	ProLine Premium Latex Dry Fall Semi-Gloss**	None	15-25@60°	225	3.0	41	54	30 Min.	1 Hr.		
	Epoxy	Semi-Gloss	Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	T.P.S. Multi-Surface Latex	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs., <30 Days		
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	Enamel Undercoater	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
	Epoxy	Gloss	Tough Coat Polyamide Catalyzed Epoxy Gloss**	(same)	80+@60°	185	4	56	70	1 Hr.	>6 Hrs., <30 Days		
			Tough Coat Modified Epoxy High Gloss Enamel**	(same)	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.		
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		

**Appropriate for use in USDA inspected facilities for incidental, indirect contact, NOT direct food contact.

EXTERIOR METAL (Continued)													
Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:			
										To Touch	To Recoat		
See prior page	Latex	Semi-Gloss	Platinum Latex Satin Gloss House Paint	Tough Coat Rust Control	35-45@60°	400	1.4	36	48	1 Hr.	4 Hrs.		
			Great Life Latex Satin Gloss House Paint	Universal Metal Primer or	35-45@60°	400	1.3	32	44	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Semi-Gloss House Paint	Super Tough Coat	35-45@60°	400	1.3	33	44	1 Hr.	4 Hrs.		
			ProLine Premium Latex Semi-Gloss House Paint	Acrylic Prime & Finish	35-45@60°	400	1.2	29	40	1 Hr.	4 Hrs.		
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.		
	Alkyd	Gloss	Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.		
			Great Life Alkyd Gloss House Paint Enamel	(same)	80+@60°	400	2.1	52	67	4-8 Hrs.	24-48 Hrs.		
			Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.		
			Tough Coat Quick Dry Alkyd Enamel**	(same)	80+@60°	465	1.0	32	46	5-10 Min.	30 Min.		
	Latex	Gloss	Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	1.5	37	46	1 Hr.	4 Hrs.		
			Epoxy	Semi-Gloss	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	(same)	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs. <30 Days
		Epoxy	Gloss		Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.
				Tough Coat Polyamide Catalyzed Epoxy Gloss**	(same)	80+@60°	185	4	56	70	1 Hr.	>6 Hrs. <30 Days	
				Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.	
				Tough Coat Modified Epoxy High Gloss Enamel**	(same)	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.	
Oleo-resin		Aluminum	Tough Coat Chrome Aluminum Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	52	3-5 Hrs.	>12 Hrs. <24 Hrs.		
Pre-Finished Metal Siding, Panels		Latex	Flat	Platinum Latex Flat House Paint	Tough Coat Rust Control	0-5@85°	400	1.4	36	50	1 Hr.	4 Hrs.	
				Great Life Latex Flat House Paint	Universal Metal Primer or	0-5@85°	400	1.3	32	46	1 Hr.	4 Hrs.	
				ProLine Supreme Latex Flat House Paint	Super Tough Coat	0-5@85°	400	1.5	38	55	1 Hr.	4 Hrs.	
	ProLine Premium Latex Flat House Paint			Acrylic Prime & Finish	0-5@85°	400	1.3	32	48	1 Hr.	4 Hrs.		
	Latex	Eggshell	Platinum Latex Eggshell House Paint	(same)	10-20@60°	400	1.5	37	49	1 Hr.	4 Hrs.		
			Great Life Latex Eggshell House Paint	(same)	10-20@60°	400	1.4	35	47	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	35	46	1 Hr.	4 Hrs.		
			ProLine Premium Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	32	41	1 Hr.	4 Hrs.		
	Latex	Semi-Gloss	Platinum Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.4	36	48	1 Hr.	4 Hrs.		
			Great Life Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.3	32	44	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.3	33	44	1 Hr.	4 Hrs.		
			ProLine Premium Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.2	29	40	1 Hr.	4 Hrs.		
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.		
			Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.		
			Great Life Alkyd Gloss House Paint	(same)	80+@60°	400	2.1	52	67	4-8 Hrs.	24-48 Hrs.		
			Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.		
	Latex	Gloss	Tough Coat Quick Dry Alkyd Enamel**	(same)	80+@60°	465	1.0	32	46	5-10 Min.	30 Min.		
			Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.		
			Epoxy	Semi-Gloss	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**		(same)	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs. <30 Days	
	Epoxy	Gloss	Tough Coat Polyamide Catalyzed Epoxy Gloss**	(same)	80+@60°	185	4	56	70	1 Hr.	>6 Hrs. <30 Days		
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
			Tough Coat Modified Epoxy High Gloss Enamel**	(same)	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.		
			Oleo-resin	Aluminum	Tough Coat Chrome Aluminum Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	52	3-5 Hrs.	>12 Hrs. <24 Hrs.
	Misc. Iron, Ornamental Iron Catwalks, Fire Escapes, Hydrants, Handrails	Latex	Semi-Gloss	Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	Tough Coat Rust Control	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.	
				Great Life Alkyd Gloss House Paint	Universal Metal Primer or	80+@60°	400	2.1	52	67	4-8 Hrs.	24-48 Hrs.	
		Alkyd	Gloss	Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	Super Tough Coat	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.	
				Tough Coat Quick Dry Alkyd Enamel**	Acrylic Prime & Finish	80+@60°	465	1.0	32	46	5-10 Min.	30 Min.	
		Latex	Gloss	Super Tough Coat DTM Acrylic Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.	
				Oleo-resin	Aluminum	Tough Coat Chrome Aluminum Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	52	3-5 Hrs.
Aluminum		Latex	Flat	Platinum Latex Flat House Paint	None	0-5@85°	400	1.4	36	50	1 Hr.	4 Hrs.	
				Great Life Latex Flat House Paint	None	0-5@85°	400	1.3	32	46	1 Hr.	4 Hrs.	
				ProLine Supreme Latex Flat House Paint	None	0-5@85°	400	1.5	38	55	1 Hr.	4 Hrs.	
				ProLine Premium Latex Flat House Paint	None	0-5@85°	400	1.3	32	48	1 Hr.	4 Hrs.	
	Latex	Eggshell	Platinum Latex Eggshell House Paint	None	10-20@60°	400	1.5	37	49	1 Hr.	4 Hrs.		
			Great Life Latex Eggshell House Paint	None	10-20@60°	400	1.4	35	47	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Eggshell House Paint	None	10-20@60°	400	1.3	35	46	1 Hr.	4 Hrs.		
			ProLine Premium Latex Eggshell House Paint	None	10-20@60°	400	1.3	32	41	1 Hr.	4 Hrs.		
	Latex	Semi-Gloss	Platinum Latex Satin Gloss House Paint	None	35-45@60°	400	1.4	36	48	1 Hr.	4 Hrs.		
			Great Life Latex Satin Gloss House Paint	None	35-45@60°	400	1.3	32	44	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Semi-Gloss House Paint	None	35-45@60°	400	1.3	33	44	1 Hr.	4 Hrs.		
			ProLine Premium Latex Semi-Gloss House Paint	None	35-45@60°	400	1.2	29	40	1 Hr.	4 Hrs.		
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	None	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.		
			Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	None	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.		
			Super Tough Coat DTM Acrylic High Gloss Enamel**	None	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.		
			Epoxy	Semi-Gloss	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	None	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.
	Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	Super Tough Coat Acrylic Prime & Finish	20-30@60°		185	5	56	70	1 Hr.	>6 Hrs. <30 Days			
	Epoxy	Gloss	Tough Coat Polyamide Catalyzed Epoxy Gloss**	(same)	80+@60°	185	4	56	70	1 Hr.	>6 Hrs. <30 Days		
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	None	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
			Tough Coat Modified Epoxy High Gloss Enamel**	None	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.		
			Leaded Copper	Alkyd	Gloss	Great Life Alkyd Gloss House Paint	Tough Coat Rust Control	80+@60°	400	2.1	52	67	4-8 Hrs.
	Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	(same)	70+@60°			400	1.7	42	58	3-5 Hrs.	12 Hrs.		
	Galvanized Metal	Latex	Flat	Platinum Latex Flat House Paint	Super Tough Coat Acrylic Prime & Finish	0-5@85°	400	1.4	36	50	1 Hr.	4 Hrs.	
				Great Life Latex Flat House Paint	(same)	0-5@85°	400	1.3	32	46	1 Hr.	4 Hrs.	
				ProLine Supreme Latex Flat House Paint	(same)	0-5@85°	400	1.5	38	55	1 Hr.	4 Hrs.	
				ProLine Premium Latex Flat House Paint	(same)	0-5@85°	400	1.3	32	48	1 Hr.	4 Hrs.	
		Latex	Eggshell	Platinum Latex Eggshell House Paint	(same)	10-20@60°	400	1.5	37	49	1 Hr.	4 Hrs.	
				Great Life Latex Eggshell House Paint	(same)	10-20@60°	400	1.4	35	47	1 Hr.	4 Hrs.	
				ProLine Supreme Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	35	46	1 Hr.	4 Hrs.	
				ProLine Premium Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	32	41	1 Hr.	4 Hrs.	
Latex		Semi-Gloss	Platinum Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.4	36	48	1 Hr.	4 Hrs.		
			Great Life Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.3	32	44	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.3	33	44	1 Hr.	4 Hrs.		
			ProLine Premium Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.2	29	40	1 Hr.	4 Hrs.		
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.		
			Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.		
			Great Life Alkyd Gloss House Paint	(same)	80+@60°	400	2.1	52	67	4-8 Hrs.	24-48 Hrs.		
			Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.		
Latex		Gloss	Tough Coat Quick Dry Alkyd Enamel**	(same)	80+@60°	465	1.0	32	46	5-10 Min.	30 Min.		
			Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.		
			Epoxy	Semi-Gloss	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.
			Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**		(same)	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs. <30 Days	
Epoxy		Gloss	Tough Coat Polyamide Catalyzed Epoxy Gloss**	(same)	80+@60°	185	4	56	70	1 Hr.	>6 Hrs. <30 Days		
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
			Tough Coat Modified Epoxy High Gloss Enamel**	(same)	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.		
			Oleo-resin	Aluminum	Tough Coat Chrome Aluminum Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	52	3-5 Hrs.	>12 Hrs. <24 Hrs.
Stacks, Breaching, Piping Under 400°F		Oleo-resin	Aluminum	Tough Coat Chrome Aluminum Alkyd High Gloss Enamel**	None	70+@60°	400	1.7	42	52	3-5 Hrs.	>12 Hrs. <24 Hrs.	

**Appropriate for use in USDA inspected facilities for incidental, indirect contact, NOT direct food contact.

Exterior Surface and Specification Selection

EXTERIOR WOOD

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Siding, Trim, Shutters, Sash, Doors, Misc. Wood	Latex	Flat	Platinum Latex Flat House Paint	T.P.S. Ext. Alkyd Wood Primer	0-5@85°	400	1.4	36	50	1 Hr.	4 Hrs.
			Great Life Latex Flat House Paint	or T.P.S. Ext. Latex Primer	0-5@85°	400	1.3	32	46	1 Hr.	4 Hrs.
			ProLine Supreme Latex Flat House Paint	(same)	0-5@85°	400	1.5	38	55	1 Hr.	4 Hrs.
			ProLine Premium Latex Flat House Paint	(same)	0-5@85°	400	1.3	32	48	1 Hr.	4 Hrs.
	Latex	Eggshell	Platinum Latex Eggshell House Paint	(same)	10-20@60°	400	1.5	37	49	1 Hr.	4 Hrs.
			Great Life Latex Eggshell House Paint	(same)	10-20@60°	400	1.4	35	47	1 Hr.	4 Hrs.
			ProLine Supreme Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	35	46	1 Hr.	4 Hrs.
			ProLine Premium Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	32	41	1 Hr.	4 Hrs.
	Latex	Semi-Gloss	Platinum Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.4	36	48	1 Hr.	4 Hrs.
			Great Life Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.3	32	44	1 Hr.	4 Hrs.
			ProLine Supreme Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.3	33	44	1 Hr.	4 Hrs.
			ProLine Premium Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.2	29	40	1 Hr.	4 Hrs.
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.
			Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.
	Alkyd	Gloss	Great Life Alkyd Gloss House Paint	(same)	80+@60°	400	2.1	52	67	4-8 Hrs.	24-48 Hrs.
			Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.
	Latex	Gloss	Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	1.5	37	46	1 Hr.	4 Hrs.
	Alkyd	Flat Stain	Great Outdoors Alkyd Semi-Trans. Deck & Siding Stain	None	0-10@85°	450	0.4	11	11	5 Hrs.	2-4 Hrs.
Great Outdoors Alkyd Solid Color Siding Stain			None	0-5@85°	350	2.3	58	77	6 Hrs.	24 Hrs.	
Latex	Flat Stain	Great Outdoors Latex Solid Color Deck Stain	None	5-15@85°	350	1.7	41	54	30 Min.	2-4 Hrs.	
		Great Outdoors Latex Solid Color Siding Stain	None	0-5@85°	400	1.3	33	49	1 Hr.	4 Hrs.	
Alkyd	Gloss Clear	Marine Spar Gloss Varnish**	Interior Oil Stain	90+@60°	550	1.8	44	51	2-3 Hrs.	18-24 Hrs.	
Shingles, Shakes, Rough Sawn Lumber	Latex	Flat	Platinum Latex Flat House Paint	T.P.S. Ext. Alkyd Wood Primer	0-5@85°	400	1.4	36	50	1 Hr.	4 Hrs.
			Great Life Latex Flat House Paint	(same)	0-5@85°	400	1.3	32	46	1 Hr.	4 Hrs.
			ProLine Supreme Latex Flat House Paint	(same)	0-5@85°	400	1.5	38	55	1 Hr.	4 Hrs.
			ProLine Premium Latex Flat House Paint	(same)	0-5@85°	400	1.3	32	48	1 Hr.	4 Hrs.
	Alkyd	Flat Stain	Great Outdoors Alkyd Semi-Trans. Deck & Siding Stain	None	0-10@85°	450	0.4	11	11	5 Hrs.	2-4 Hrs.
			Great Outdoors Alkyd Solid Color Siding Stain	None	0-5@85°	350	2.3	58	77	6 Hrs.	24 Hrs.
Latex	Flat Stain	Great Outdoors Latex Solid Color Deck Stain	None	5-15@85°	350	1.7	41	55	30 Min.	24 Hrs.	
		Great Outdoors Latex Solid Color Siding Stain	None	0-5@60°	400	1.3	33	49	1 Hr.	2-4 Hrs.	
Floors, Dadoes, Platforms	Latex	Satin	Latex Floor, Porch & Trim Enamel**	T.P.S. Ext. Alkyd Wood Primer	10-20@60°	400	1.2	30	36	1-2 Hrs.	12 Hrs.
			Alkyd Floor, Porch & Trim Enamel**	None	70+@60°	400	2.2	55	70	1-3 Hrs.	24 Hrs.
	Epoxy	Gloss	Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	None	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.
			Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	None	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs. <30 Days
Plywood	Latex	Flat	Platinum Latex Flat House Paint	T.P.S. Ext. Latex Primer	0-5@85°	400	1.4	36	50	1 Hr.	4 Hrs.
			Great Life Latex Flat House Paint	(same)	0-5@85°	400	1.3	32	46	1 Hr.	4 Hrs.
			ProLine Supreme Latex Flat House Paint	(same)	0-5@85°	400	1.5	38	55	1 Hr.	4 Hrs.
			ProLine Premium Latex Flat House Paint	(same)	0-5@85°	400	1.3	32	48	1 Hr.	4 Hrs.
	Latex	Eggshell	Platinum Latex Eggshell House Paint	(same)	10-20@60°	400	1.5	37	49	1 Hr.	4 Hrs.
			Great Life Latex Eggshell House Paint	(same)	10-20@60°	400	1.4	35	47	1 Hr.	4 Hrs.
			ProLine Supreme Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	35	46	1 Hr.	4 Hrs.
			ProLine Premium Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	32	41	1 Hr.	4 Hrs.
	Latex	Semi-Gloss	Platinum Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.4	36	48	1 Hr.	4 Hrs.
			Great Life Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.3	32	44	1 Hr.	4 Hrs.
Alkyd	Flat Stain	ProLine Supreme Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.3	33	44	1 Hr.	4 Hrs.	
		ProLine Premium Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.2	29	40	1 Hr.	4 Hrs.	
Latex	Flat Stain	Great Outdoors Alkyd Semi-Trans. Deck & Siding Stain	None	0-10@85°	450	0.4	11	11	5 Hrs.	2-4 Hrs.	
		Great Outdoors Latex Solid Color Deck Stain	None	5-15@85°	350	1.7	41	55	30 Min.	24 Hrs.	
			Great Outdoors Latex Solid Color Siding Stain	None	0-5@60°	400	1.3	33	49	1 Hr.	2-4 Hrs.

EXTERIOR METAL

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Structural Iron & Steel, Tanks, Sash, Trim, Conductors, Doors, Ducts, Vents (not galvanized)	Latex	Flat	Platinum Latex Flat House Paint	Tough Coat Rust Control	0-5@85°	400	1.4	36	50	1 Hr.	4 Hrs.
			Great Life Latex Flat House Paint	Universal Metal Primer	0-5@85°	400	1.3	32	46	1 Hr.	4 Hrs.
			ProLine Supreme Latex Flat House Paint	or Super Tough Coat	0-5@85°	400	1.5	38	55	1 Hr.	4 Hrs.
			ProLine Premium Latex Flat House Paint	Acrylic Prime & Finish	0-5@85°	400	1.3	32	48	1 Hr.	4 Hrs.
	Latex	Eggshell	Platinum Latex Eggshell House Paint	(same)	10-20@60°	400	1.5	37	49	1 Hr.	4 Hrs.
			Great Life Latex Eggshell House Paint	(same)	10-20@60°	400	1.4	35	47	1 Hr.	4 Hrs.
			ProLine Supreme Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	35	46	1 Hr.	4 Hrs.
			ProLine Premium Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	32	41	1 Hr.	4 Hrs.

**Appropriate for use in USDA inspected facilities for incidental, indirect contact, NOT direct food contact.

INTERIOR WOOD

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:			
										To Touch	To Recoat		
Ceilings, Doors, Trim, Cabinets, Work Partitions, Frames	Alkyd Latex	Flat	ProLine Premium Alkyd Flat Wall Paint**	T.P.S. Multi-Surface Latex Enamel Undercoater or	0-10@85°	400	2.0	49	74	2-5 Hrs.	24 Hrs.		
			Platinum Latex Flat Wall Paint**	(same)	0-5@85°	400	1.6	40	56	1 Hr.	4 Hrs.		
			Bright Life Latex Flat Wall Paint**	T.P.S. Alkyd Enamel Undercoater	0-5@85°	400	1.6	41	58	1 Hr.	4 Hrs.		
			ProLine Supreme Low Odor Latex Flat Wall Paint**	(same)	0-5@85°	400	1.7	42	60	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Flat Wall Paint**	(same)	0-2@85°	400	1.4	34	53	1 Hr.	4 Hrs.		
			ProLine Premium Latex Flat Wall Paint**	(same)	0-5@85°	400	1.3	32	50	1 Hr.	4 Hrs.		
			Latex Ceiling Paint "Best"***	(same)	0-5@85°	400	1.2	31	50	1 Hr.	4 Hrs.		
			Latex Ceiling Paint "Better"***	(same)	0-5@85°	400	1.1	28	46	1 Hr.	4 Hrs.		
			ProLine Premium Alkyd Eggshell Enamel**	(same)	20-30@60°	400	1.8	44	65	2-5 Hrs.	24 Hrs.		
	Alkyd Latex	Eggshell	Platinum Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	40	55	1 Hr.	4 Hrs.		
			Bright Life Latex Eggshell Enamel**	(same)	10-20@85°	400	1.3	33	47	1 Hr.	4 Hrs.		
			ProLine Supreme Low Odor Latex Eggshell Enamel**	(same)	10-20@85°	400	1.6	39	53	1 Hr.	4 Hrs.		
			ProLine Supreme Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	39	52	1 Hr.	4 Hrs.		
			ProLine Premium Latex Eggshell Enamel**	(same)	15-20@85°	400	1.2	30	44	1 Hr.	4 Hrs.		
			Alkyd Latex	Semi-Gloss	Platinum Alkyd Satin Gloss Enamel**	(same)	25-35@60°	350-400	2.3	54	72	2-4 Hrs.	24 Hrs.
					Bright Life Alkyd Satin Gloss Enamel**	(same)	55-65@60°	400	1.7	43	63	2-4 Hrs.	24 Hrs.
					ProLine Premium Alkyd Semi-Gloss Enamel**	(same)	55-65@60°	400	1.6	40	60	2-5 Hrs.	24 Hrs.
					Platinum Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.6	39	52	1 Hr.	4 Hrs.
	Kitchen, Bath & Trim Acrylic Semi-Gloss Enamel**	(same)			30-40@60°	200-300	3	38	50	1 Hr.	4 Hrs.		
	Bright Life Latex Satin Gloss Enamel**	(same)			25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.		
	ProLine Supreme Low Odor Latex Semi-Gloss Enamel**	(same)			35-45@60°	400	1.6	40	48	1 Hr.	4 Hrs.		
	ProLine Supreme Latex Semi-Gloss Enamel**	(same)			25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.		
	ProLine Premium Latex Semi-Gloss Enamel**	(same)			25-35@60°	400	1.2	30	38	1 Hr.	4 Hrs.		
	Alkyd Latex	Semi-Gloss	Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.		
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	1.5	38	50	1 Hr.	4 Hrs.		
			Bright Life Alkyd Gloss Enamel**	(same)	80+@60°	400	1.6	39	56	2-4 Hrs.	24 Hrs.		
			Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.		
			Tough Coat Quick Dry Alkyd Enamel**	None	80+@60°	465	1.0	30	44	5-10 Min.	30 Min.		
			Bright Life Latex High Gloss Enamel**	(same)	60-80@60°	400	1.5	38	48	1 Hr.	4 Hrs.		
			Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.		
			ProLine Premium Alkyd Dry Fall Flat**	(same)	0-8@85°	295	3.3	55	80	10 Min.	2-6 Hrs.		
			ProLine Premium Latex Dry Fall Flat**	(same)	0-10@85°	225	3.0	42	60	30 Min.	1 Hr.		
	Alkyd Latex	Flat	ProLine Premium Alkyd Dry Fall Semi-Gloss**	(same)	18-28@60°	260	2.9	49	71	10 Min.	2-6 Hrs.		
			ProLine Premium Latex Dry Fall Semi-Gloss**	(same)	15-25@60°	225	3.0	41	54	30 Min.	1 Hr.		
			Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	None	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs. <30 Days		
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
			Tough Coat Polyamide Catalyzed Epoxy Gloss**	None	80+@60°	185	4	56	70	1 Hr.	>6 Hrs. <30 Days		
			Tough Coat Modified Epoxy High Gloss Enamel**	(same)	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.		
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
			Latex Floor, Porch & Trim Enamel**	(same)	10-20@60°	400	1.2	30	36	1-2 Hrs.	12 Hrs.		
			Alkyd Floor, Porch & Trim Enamel**	None	70+@60°	400	2.2	55	70	1-3 Hrs.	24 Hrs.		
	Wood Floors - Painted	Alkyd	Gloss	Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	None	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.	
				Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	None	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs. <30 Days	
				Tough Coat Polyamide Catalyzed Epoxy Gloss**	None	80+@60°	185	4	56	70	1 Hr.	>6 Hrs. <30 Days	
	Floors - Stained, Varnished	Polyur.	Gloss	Astro Var Satin Varnish**	Int. Oil Stain (Opt.)	20-30@60°	500	1.5	36	44	2 Hrs.	>12 Hrs. <48 Hrs.	
Astro Var Gloss Varnish**				Int. Oil Stain (Opt.)	90+@60°	500	1.7	43	50	2 Hrs.	>12 Hrs. <48 Hrs.		
Astro Var Gloss Varnish**				Int. Oil Stain (Opt.)	90+@60°	500	1.7	43	50	2 Hrs.	>12 Hrs. <48 Hrs.		
Floors - Gym (new)	Polyur.	Gloss	Astro Var Gloss Varnish**	Int. Oil Stain (Opt.)	90+@60°	500	1.7	43	50	2 Hrs.	>12 Hrs. <48 Hrs.		

INTERIOR ACOUSTICAL

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:		
										To Touch	To Recoat	
Perforated Fiberboard	Alkyd Latex	Flat	ProLine Premium Alkyd Flat Wall Paint**	T.P.S. Multi-Surface Latex Enamel Undercoater or	0-10@85°	400	2.0	49	74	2-5 Hrs.	24 Hrs.	
			ProLine Premium Alkyd Dry Fall Flat**	(same)	0-8@85°	295	3.3	55	80	10 Min.	2-6 Hrs.	
			Platinum Latex Flat Wall Paint**	T.P.S. Latex Wall Primer	0-5@85°	400	1.6	40	56	1 Hr.	4 Hrs.	
			Bright Life Latex Flat Wall Paint**	(same)	0-5@85°	400	1.6	41	58	1 Hr.	4 Hrs.	
			ProLine Supreme Low Odor Latex Flat Wall Paint**	(same)	0-5@85°	400	1.7	42	60	1 Hr.	4 Hrs.	
			ProLine Supreme Latex Flat Wall Paint**	(same)	0-2@85°	400	1.4	34	53	1 Hr.	4 Hrs.	
			ProLine Premium Latex Flat Wall Paint**	(same)	0-5@85°	400	1.3	32	50	1 Hr.	4 Hrs.	
			Latex Ceiling Paint "Best"***	(same)	0-5@85°	400	1.2	31	50	1 Hr.	4 Hrs.	
			Latex Ceiling Paint "Better"***	(same)	0-5@85°	400	1.1	28	46	1 Hr.	4 Hrs.	
	ProLine Premium Latex Dry Fall Flat**	None	0-10@85°	225	3.0	42	60	30 Min.	1 Hr.			
	Metalpan, Acoustical Tile	Alkyd Latex	Flat	ProLine Premium Alkyd Flat Wall Paint**	T.P.S. Alkyd Enamel Undercoater	0-10@85°	400	2.0	49	74	2-5 Hrs.	24 Hrs.
				ProLine Premium Alkyd Dry Fall Flat**	(same)	0-8@85°	295	3.3	55	80	10 Min.	2-6 Hrs.
				Platinum Latex Flat Wall Paint**	(same)	0-5@85°	400	1.6	40	56	1 Hr.	4 Hrs.
				Bright Life Latex Flat Wall Paint**	(same)	0-5@85°	400	1.6	41	58	1 Hr.	4 Hrs.
				ProLine Supreme Low Odor Latex Flat Wall Paint**	(same)	0-5@85°	400	1.7	42	60	1 Hr.	4 Hrs.
ProLine Supreme Latex Flat Wall Paint**				(same)	0-2@85°	400	1.4	34	53	1 Hr.	4 Hrs.	
Metalpan, Acoustical Tile	Alkyd Latex	Flat	ProLine Premium Latex Flat Wall Paint**	(same)	0-5@85°	400	1.3	32	50	1 Hr.	4 Hrs.	
			Latex Ceiling Paint "Best"***	(same)	0-5@85°	400	1.2	31	50	1 Hr.	4 Hrs.	
			Latex Ceiling Paint "Better"***	(same)	0-5@85°	400	1.1	28	46	1 Hr.	4 Hrs.	
			ProLine Premium Latex Dry Fall Flat**	(same)	0-5@85°	400	1.1	28	46	1 Hr.	4 Hrs.	
			ProLine Premium Latex Dry Fall Flat**	(same)	0-10@85°	225	3.0	42	60	30 Min.	1 Hr.	
			ProLine Premium Latex Dry Fall Flat**	(same)	0-10@85°	225	3.0	42	60	30 Min.	1 Hr.	

**Appropriate for use in USDA inspected facilities for incidental, indirect contact, NOT direct food contact.

Interior Surface and Specification Selection

INTERIOR MASONRY

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Walls & Ceilings, Concrete Block, Poured Concrete, Precast Concrete, Unglazed Brick & Tile	Alkyd Latex	Flat	ProLine Premium Alkyd Flat Wall Paint**	T.P.S. Multi-Surface Latex	0-10@85°	400	2.0	49	74	2-5 Hrs.	24 Hrs.
			Platinum Latex Flat Wall Paint**	Enamel Undercoater or	0-5@85°	400	1.6	40	56	1 Hr.	4 Hrs.
	Alkyd Latex	Eggshell	Bright Life Latex Flat Wall Paint**	T.P.S. Latex Wall Primer or	0-5@85°	400	1.6	41	58	1 Hr.	4 Hrs.
			ProLine Supreme Low Odor Latex Flat Wall Paint**	Pro Line Premium Heavy Duty	0-5@85°	400	1.7	42	60	1 Hr.	4 Hrs.
			ProLine Supreme Latex Flat Wall Paint**	Block Filler (for block)	0-2@85°	400	1.4	34	53	1 Hr.	4 Hrs.
			ProLine Premium Latex Flat Wall Paint**	(same)	0-5@85°	400	1.3	32	50	1 Hr.	4 Hrs.
			Latex Ceiling Paint "Best"***	(same)	0-5@85°	400	1.2	31	50	1 Hr.	4 Hrs.
			Latex Ceiling Paint "Better"***	(same)	0-5@85°	400	1.1	28	46	1 Hr.	4 Hrs.
			ProLine Premium Alkyd Eggshell Enamel**	(same)	20-30@60°	400	1.8	44	65	2-5 Hrs.	24 Hrs.
			Platinum Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	40	55	1 Hr.	4 Hrs.
			Bright Life Latex Eggshell Enamel**	(same)	10-20@85°	400	1.3	33	47	1 Hr.	4 Hrs.
			ProLine Supreme Low Odor Latex Eggshell Enamel**	(same)	10-20@85°	400	1.6	39	53	1 Hr.	4 Hrs.
	Alkyd Latex	Semi-Gloss	ProLine Supreme Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	39	52	1 Hr.	4 Hrs.
			ProLine Premium Latex Eggshell Enamel**	(same)	15-20@85°	400	1.2	30	44	1 Hr.	4 Hrs.
			Platinum Alkyd Satin Gloss Enamel**	(same)	25-35@60°	350-400	2.3	54	72	2-4 Hrs.	24 Hrs.
			Bright Life Alkyd Satin Gloss Enamel**	(same)	55-65@60°	400	1.7	43	63	2-4 Hrs.	24 Hrs.
			ProLine Premium Alkyd Semi-Gloss Enamel**	(same)	55-65@60°	400	1.6	40	60	2-5 Hrs.	24 Hrs.
			Kitchen, Bath & Trim Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	200-300	3	38	50	1 Hr.	4 Hrs.
			Platinum Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.6	39	52	1 Hr.	4 Hrs.
			Bright Life Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.
			ProLine Supreme Low Odor Latex Semi-Gloss Enamel**	(same)	35-45@60°	400	1.6	40	48	1 Hr.	4 Hrs.
			ProLine Supreme Latex Semi-Gloss Enamel**	(same)	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.
	Alkyd Latex	Gloss	ProLine Premium Latex Semi-Gloss Enamel**	(same)	25-35@60°	400	1.2	30	38	1 Hr.	4 Hrs.
			Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.
			Bright Life Alkyd Gloss Enamel**	(same)	80+@60°	400	1.6	39	56	2-4 Hrs.	24 Hrs.
			Tough Coat Heavy Duty Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.
			Bright Life Latex High Gloss Enamel**	(same)	60-80@60°	400	1.5	38	48	1 Hr.	24 Hrs.
			Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.
			ProLine Premium Alkyd Dry Fall Flat**	(same)	0-8@85°	295	3.3	55	80	10 Min.	2-6 Hrs.
			ProLine Premium Latex Dry Fall Flat**	(same)	0-10@85°	225	3.0	42	60	30 Min.	1 Hr.
			ProLine Premium Alkyd Dry Fall Semi-Gloss**	(same)	18-28@60°	260	2.9	49	71	10 Min.	2-6 Hrs.
	Epoxy	Semi-Gloss	ProLine Premium Latex Dry Fall Semi-Gloss**	(same)	15-25@60°	225	3.0	41	54	30 Min.	1 Hr.
			Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	None (Pro Line Premium Heavy-Duty)	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs. <30 Days
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	Block Filler [for block]	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.
			Tough Coat Polyamide Catalyzed Epoxy Gloss**	(same)	80+@60°	185	4	56	70	1 Hr.	>6 Hrs. <30 Days
Tough Coat Modified Epoxy High Gloss Enamel**			(same)	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.	
Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**			(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.	
Latex Floor, Porch & Trim Enamel**			None	10-20@60°	400	1.2	30	36	1-2 Hrs.	12 Hrs.	
Alkyd Floor, Porch & Trim Enamel**			None	70+@60°	400	2.2	55	70	1-3 Hrs.	24 Hrs.	
Tough Coat Heavy-Duty Alkyd High Gloss Enamel**			None	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.	
Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**			None	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs. <30 Days	
Floors	Epoxy	Gloss	Tough Coat Polyamide Catalyzed Epoxy Gloss**	None	80+@60°	185	4	56	70	1 Hr.	>6 Hrs. <30 Days

INTERIOR METAL

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Walls, Ceilings, Structural Steel, Ornamental Iron Trim, Doors, Windows, Lockers, Machine, Equip., Ducts, Copper, Non-Galvanized Metal	Alkyd Latex	Flat	ProLine Premium Alkyd Flat Wall Paint**	Tough Coat Rust Control	0-10@85°	400	2.0	49	74	2-5 Hrs.	24 Hrs.
			Platinum Latex Flat Wall Paint**	Universal Metal Primer or	0-5@85°	400	1.6	40	56	1 Hr.	4 Hrs.
	Alkyd Latex	Eggshell	Bright Life Latex Flat Wall Paint**	Super Tough Coat Acrylic	0-5@85°	400	1.6	41	58	1 Hr.	4 Hrs.
			ProLine Supreme Low Odor Latex Flat Wall Paint**	Prime & Finish	0-5@85°	400	1.7	42	60	1 Hr.	4 Hrs.
			ProLine Supreme Latex Flat Wall Paint**	(same)	0-2@85°	400	1.4	34	53	1 Hr.	4 Hrs.
			ProLine Premium Latex Flat Wall Paint**	(same)	0-5@85°	400	1.3	32	50	1 Hr.	4 Hrs.
			Latex Ceiling Paint "Best"***	(same)	0-5@85°	400	1.2	31	50	1 Hr.	4 Hrs.
			Latex Ceiling Paint "Better"***	(same)	0-5@85°	400	1.1	28	46	1 Hr.	4 Hrs.
			ProLine Premium Alkyd Eggshell Enamel**	(same)	20-30@60°	400	1.8	44	65	2-5 Hrs.	24 Hrs.
			Platinum Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	40	55	1 Hr.	4 Hrs.
			Bright Life Latex Eggshell Enamel**	(same)	10-20@85°	400	1.3	33	47	1 Hr.	4 Hrs.
			ProLine Supreme Low Odor Latex Eggshell Enamel**	(same)	10-20@85°	400	1.6	39	53	1 Hr.	4 Hrs.
	Alkyd Latex	Semi-Gloss	ProLine Supreme Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	39	52	1 Hr.	4 Hrs.
			ProLine Premium Latex Eggshell Enamel**	(same)	15-20@85°	400	1.2	30	44	1 Hr.	4 Hrs.
			Platinum Alkyd Satin Gloss Enamel**	(same)	25-35@60°	350-400	2.3	54	72	2-4 Hrs.	24 Hrs.
			Bright Life Alkyd Satin Gloss Enamel**	(same)	55-65@60°	400	1.7	43	63	2-4 Hrs.	24 Hrs.
			ProLine Premium Alkyd Semi-Gloss Enamel**	(same)	55-65@60°	400	1.6	40	60	2-5 Hrs.	24 Hrs.
			Platinum Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.6	39	52	1 Hr.	4 Hrs.
			Kitchen, Bath & Trim Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	200-300	3	38	50	1 Hr.	4 Hrs.
			Bright Life Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.
			ProLine Supreme Low Odor Latex Semi-Gloss Enamel**	(same)	35-45@60°	400	1.6	40	48	1 Hr.	4 Hrs.
			ProLine Supreme Latex Semi-Gloss Enamel**	(same)	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.
	Alkyd Latex	Semi-Gloss	ProLine Premium Latex Semi-Gloss Enamel**	(same)	25-35@60°	400	1.2	30	38	1 Hr.	4 Hrs.
			Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.

** Appropriate for use in USDA inspected facilities for incidental, indirect contact, NOT direct food contact.

INTERIOR METAL (Continued)

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft./Gal. (smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:		
										To Touch	To Recoat	
See prior page	Alkyd	Gloss	Bright Life Alkyd Gloss Enamel**	Tough Coat Rust Control	80+@60°	400	1.6	39	56	2-4 Hrs.	24 Hrs.	
			Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	Universal Metal Primer or Super Tough Coat Acrylic	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.	
	Latex	Gloss	Tough Coat Quick Dry Alkyd Enamel**	Prime & Finish	80+@60°	465	1.0	32	46	5-10 Min.	30 Min.	
			Bright Life Latex High Gloss Enamel**	(same)	60-80@60°	400	1.5	38	48	1 Hr.	4 Hrs.	
	Alkyd	Flat	Super Tough Coat DTM Acrylic Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.	
			Pro Line Premium Alkyd Dry Fall Flat**	(same)	0-8@85°	295	3.3	55	80	10 Min.	2-6 Hrs.	
	Latex	Flat	Pro Line Premium Latex Dry Fall Flat**	(same)	0-10@85°	225	3.0	42	60	30 Min.	1 Hr.	
			Pro Line Premium Alkyd Dry Fall Semi-Gloss**	(same)	18-28@60°	260	2.9	49	71	10 Min.	2-6 Hrs.	
	Latex	Semi-Gloss	Pro Line Premium Latex Dry Fall Semi-Gloss**	(same)	15-25@60°	225	3.0	41	54	30 Min.	1 Hr.	
			Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	(same)	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs., <30 Days	
	Epoxy	Semi-Gloss	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.	
			Tough Coat Polyamide Catalyzed Epoxy Gloss**	(same)	80+@60°	185	4	56	70	1 Hr.	>6 Hrs., <30 Days	
	Epoxy	Gloss	Tough Coat Modified Epoxy High Gloss Enamel**	(same)	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.	
			Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.	
	Oleo-resin.	Aluminum	Tough Coat Chrome Aluminum Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	52	3-5 Hrs.	>12 Hrs., <24 Hrs.	
	Galvanized Metal	Alkyd	Flat	Pro Line Premium Alkyd Flat Wall Paint**	T.P.S. Acrylic Latex Bonding Primer or Super Tough Coat	0-10@85°	400	2.0	49	74	2-5 Hrs.	24 Hrs.
				Platinum Latex Flat Wall Paint**	Acrylic Prime & Finish	0-5@85°	400	1.6	40	56	1 Hr.	4 Hrs.
		Latex	Flat	Bright Life Latex Flat Wall Paint**	(same)	0-5@85°	400	1.6	41	58	1 Hr.	4 Hrs.
				Pro Line Supreme Low Odor Latex Flat Wall Paint**	(same)	0-5@85°	400	1.7	42	60	1 Hr.	4 Hrs.
Alkyd		Eggshell	Pro Line Supreme Latex Flat Wall Paint**	(same)	0-2@85°	400	1.4	34	53	1 Hr.	4 Hrs.	
			Pro Line Premium Latex Flat Wall Paint**	(same)	0-5@85°	400	1.3	32	50	1 Hr.	4 Hrs.	
Latex		Eggshell	Latex Ceiling Paint "Best"***	(same)	0-5@85°	400	1.2	31	50	1 Hr.	4 Hrs.	
			Latex Ceiling Paint "Better"***	(same)	0-5@85°	400	1.1	28	46	1 Hr.	4 Hrs.	
Alkyd		Eggshell	Pro Line Premium Alkyd Eggshell Enamel**	(same)	20-30@60°	400	1.8	44	65	2-5 Hrs.	24 Hrs.	
			Platinum Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	40	55	1 Hr.	4 Hrs.	
Latex		Eggshell	Bright Life Latex Eggshell Enamel**	(same)	10-20@85°	400	1.3	33	47	1 Hr.	4 Hrs.	
			Pro Line Supreme Low Odor Latex Eggshell Enamel**	(same)	10-20@85°	400	1.6	39	53	1 Hr.	4 Hrs.	
Alkyd		Semi-Gloss	Pro Line Supreme Latex Eggshell Enamel**	(same)	15-20@85°	400	1.6	39	52	1 Hr.	4 Hrs.	
			Pro Line Premium Latex Eggshell Enamel**	(same)	15-20@85°	400	1.2	30	44	1 Hr.	4 Hrs.	
Alkyd		Semi-Gloss	Platinum Alkyd Satin Gloss Enamel**	(same)	25-35@60°	350-400	2.3	54	72	2-4 Hrs.	24 Hrs.	
			Bright Life Alkyd Satin Gloss Enamel**	(same)	55-65@60°	400	1.7	43	63	2-4 Hrs.	24 Hrs.	
Latex		Semi-Gloss	Pro Line Premium Alkyd Semi-Gloss Enamel**	(same)	55-65@60°	400	1.6	40	60	2-5 Hrs.	24 Hrs.	
			Platinum Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.6	39	52	1 Hr.	4 Hrs.	
Alkyd		Gloss	Kitchen, Bath & Trim Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	200-300	3	38	50	1 Hr.	4 Hrs.	
			Bright Life Latex Satin Gloss Enamel**	(same)	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.	
Latex	Gloss	Pro Line Supreme Low Odor Latex Semi-Gloss Enamel**	(same)	35-45@60°	400	1.6	40	48	1 Hr.	4 Hrs.		
		Pro Line Supreme Latex Semi-Gloss Enamel**	(same)	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.		
Alkyd	Gloss	Pro Line Premium Latex Semi-Gloss Enamel**	(same)	25-35@60°	400	1.2	30	38	1 Hr.	4 Hrs.		
		Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	None	30-50@60°	395	1.5	36	46	30 Min.	4 Hrs.		
Latex	Gloss	Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	None	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.		
		Bright Life Alkyd Gloss Enamel**	(same)	80+@60°	400	1.6	39	56	2-4 Hrs.	24 Hrs.		
Alkyd	Gloss	Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.		
		Tough Coat Quick Dry Alkyd Enamel**	(same)	80+@60°	465	1.0	32	46	5-10 Min.	30 Min.		
Latex	Gloss	Bright Life Latex High Gloss Enamel**	(same)	60-80@60°	400	1.5	38	48	1 Hr.	4 Hrs.		
		Super Tough Coat DTM Acrylic Gloss Enamel**	None	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.		
Alkyd	Flat	Pro Line Premium Alkyd Dry Fall Flat**	(same)	0-8@85°	295	3.3	55	80	10 Min.	2-6 Hrs.		
		Pro Line Premium Latex Dry Fall Flat**	None	0-10@85°	225	3.0	42	60	30 Min.	1 Hr.		
Alkyd	Semi-Gloss	Pro Line Premium Alkyd Dry Fall Semi-Gloss**	(same)	18-28@60°	260	2.9	49	71	10 Min.	2-6 Hrs.		
		Pro Line Premium Latex Dry Fall Semi-Gloss**	None	15-25@60°	225	3.0	41	54	30 Min.	1 Hr.		
Epoxy	Semi-Gloss	Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	(same)	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs., <30 Days		
		Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
Epoxy	Gloss	Tough Coat Polyamide Catalyzed Epoxy Gloss**	(same)	80+@60°	185	4	56	70	1 Hr.	>6 Hrs., <30 Days		
		Tough Coat Modified Epoxy High Gloss Enamel**	(same)	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.		
Oleo-resin.	Aluminum	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
		Tough Coat Chrome Aluminum Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	52	3-5 Hrs.	>12 Hrs., <24 Hrs.		
Aluminum	Alkyd	Flat	Pro Line Premium Alkyd Flat Wall Paint**	T.P.S. Acrylic Latex Bonding Primer or Super Tough Coat Acrylic Prime and Finish	0-10@85°	400	2.0	49	74	2-5 Hrs.	24 Hrs.	
			Platinum Latex Flat Wall Paint**	None	0-5@85°	400	1.6	40	56	1 Hr.	4 Hrs.	
	Latex	Flat	Bright Life Latex Flat Wall Paint**	None	0-5@85°	400	1.6	41	58	1 Hr.	4 Hrs.	
			Pro Line Supreme Low Odor Latex Flat Wall Paint**	None	0-5@85°	400	1.7	42	60	1 Hr.	4 Hrs.	
	Alkyd	Eggshell	Pro Line Supreme Latex Flat Wall Paint**	None	0-2@85°	400	1.4	34	53	1 Hr.	4 Hrs.	
			Pro Line Premium Latex Flat Wall Paint**	None	0-5@85°	400	1.3	32	50	1 Hr.	4 Hrs.	
	Latex	Eggshell	Latex Ceiling Paint "Best"***	None	0-5@85°	400	1.2	31	50	1 Hr.	4 Hrs.	
			Latex Ceiling Paint "Better"***	None	0-5@85°	400	1.1	28	46	1 Hr.	4 Hrs.	
	Alkyd	Eggshell	Pro Line Premium Alkyd Eggshell Enamel**	(same)	20-30@60°	400	1.8	44	65	2-5 Hrs.	24 Hrs.	
			Platinum Latex Eggshell Enamel**	None	15-20@85°	400	1.6	40	55	1 Hr.	4 Hrs.	
	Latex	Eggshell	Bright Life Latex Eggshell Enamel**	None	10-20@85°	400	1.3	33	47	1 Hr.	4 Hrs.	
			Pro Line Supreme Low Odor Latex Eggshell Enamel**	None	10-20@85°	400	1.6	39	53	1 Hr.	4 Hrs.	
	Alkyd	Semi-Gloss	Pro Line Supreme Latex Eggshell Enamel**	None	15-20@85°	400	1.6	39	52	1 Hr.	4 Hrs.	
			Pro Line Premium Latex Eggshell Enamel**	None	15-20@85°	400	1.2	30	44	1 Hr.	4 Hrs.	
	Latex	Semi-Gloss	Platinum Alkyd Satin Gloss Enamel**	(same)	25-35@60°	350-400	2.3	54	72	2-4 Hrs.	24 Hrs.	
			Bright Life Alkyd Satin Gloss Enamel**	(same)	55-65@60°	400	1.7	43	63	2-4 Hrs.	24 Hrs.	
	Alkyd	Gloss	Pro Line Premium Alkyd Semi-Gloss Enamel**	(same)	55-65@60°	400	1.6	40	60	2-5 Hrs.	24 Hrs.	
			Platinum Latex Satin Gloss Enamel**	None	25-35@60°	400	1.6	39	52	1 Hr.	4 Hrs.	
	Latex	Gloss	Kitchen, Bath & Trim Acrylic Semi-Gloss Enamel**	None	30-40@60°	200-300	3	38	50	1 Hr.	4 Hrs.	
			Bright Life Latex Satin Gloss Enamel**	None	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.	
Alkyd	Semi-Gloss	Pro Line Supreme Low Odor Latex Semi-Gloss Enamel**	None	35-45@60°	400	1.6	40	48	1 Hr.	4 Hrs.		
		Pro Line Supreme Latex Semi-Gloss Enamel**	None	25-35@60°	400	1.5	38	46	1 Hr.	4 Hrs.		
Latex	Semi-Gloss	Pro Line Premium Latex Semi-Gloss Enamel**	None	25-35@60°	400	1.2	30	38	1 Hr.	4 Hrs.		
		Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	None	30-50@60°	395	1.5	36	46	30 Min.	4 Hrs.		
Alkyd	Gloss	Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	None	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.		
		Bright Life Alkyd Gloss Enamel**	(same)	80+@60°	400	1.6	39	56	2-4 Hrs.	24 Hrs.		
Latex	Gloss	Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	(same)	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.		
		Tough Coat Quick Dry Alkyd Enamel**	(same)	80+@60°	465	1.0	32	46	5-10 Min.	30 Min.		
Alkyd	Flat	Bright Life Latex High Gloss Enamel**	None	60-80@60°	400	1.5	38	48	1 Hr.	4 Hrs.		
		Super Tough Coat DTM Acrylic Gloss Enamel**	None	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.		
Alkyd	Flat	Pro Line Premium Alkyd Dry Fall Flat**	(same)	0-8@85°	295	3.3	55	80	10 Min.	2-6 Hrs.		
		Pro Line Premium Latex Dry Fall Flat**	None	0-10@85°	225	3.0	42	60	30 Min.	1 Hr.		
Alkyd	Semi-Gloss	Pro Line Premium Alkyd Dry Fall Semi-Gloss**	(same)	18-28@60°	260	2.9	49	71	10 Min.	2-6 Hrs.		
		Pro Line Premium Latex Dry Fall Semi-Gloss**	None	15-25@60°	225	3.0	41	54	30 Min.	1 Hr.		
Epoxy	Semi-Gloss	Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	(same)	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs., <30 Days		
		Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	None	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
Epoxy	Gloss	Tough Coat Polyamide Catalyzed Epoxy Gloss**	(same)	80+@60°	185	4	56	70	1 Hr.	>6 Hrs., <30 Days		
		Tough Coat Modified Epoxy High Gloss Enamel**	None	80+@60°	295	1.9	37	54	2 Hrs.	18 Hrs.		
Oleo-resin.	Aluminum	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	None	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.		
		Tough Coat Chrome Aluminum Alkyd High Gloss Enamel**	None	70+@60°	400	1.7	42	52	3-5 Hrs.	>12 Hrs., <24 Hrs.		
Heat-Res. Under 400°F	Aluminum	Tough Coat Chrome Aluminum Alkyd High Gloss Enamel**	None	70+@60°	400	1.7	42	52	3-5 Hrs.	>12 Hrs., <24 Hrs.		

EXTERIOR MASONRY

Surface & Area	Veh.	Sheen	Finished Coat	Primer	Gloss Units	Sq.ft/Gal. (Smooth)	Mils DFT	% Solids By Vol.	% Solids By Wt.	Drying Time:	
										To Touch	To Recoat
Cinder & Concrete Block	Latex	Flat	Platinum Latex Flat House Paint	ProLine Premium	0-5@85°	400	1.4	36	50	1 Hr.	4 Hrs.
			Great Life Latex Flat House Paint	Heavy-Duty Block	0-5@85°	400	1.3	32	46	1 Hr.	4 Hrs.
			ProLine Supreme Latex Flat House Paint	Filler or Stretch Coat	0-5@85°	400	1.5	38	55	1 Hr.	4 Hrs.
			ProLine Premium Latex Flat House Paint	Acrylic Masonry Primer	0-5@85°	400	1.3	32	48	1 Hr.	4 Hrs.
	Latex	Eggshell	Platinum Latex Eggshell House Paint	(same)	10-20@60°	400	1.5	37	49	1 Hr.	4 Hrs.
			Great Life Latex Eggshell House Paint	(same)	10-20@60°	400	1.4	35	47	1 Hr.	4 Hrs.
			ProLine Supreme Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	35	46	1 Hr.	4 Hrs.
			ProLine Premium Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	32	41	1 Hr.	4 Hrs.
	Latex	Semi-Gloss	Platinum Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.4	36	48	1 Hr.	4 Hrs.
			Great Life Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.3	32	44	1 Hr.	4 Hrs.
			ProLine Supreme Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.3	33	44	1 Hr.	4 Hrs.
			ProLine Premium Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.2	29	40	1 Hr.	4 Hrs.
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.
			Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.
	Latex	Gloss	Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.
			Epoxy Semi-Gloss	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.
	Epoxy	Gloss	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.
			Latex	Satin	Latex Floor, Porch & Trim Enamel**	Reduce First Coat	10-20@60°	400	1.2	30	36
Concrete Floors, Patios, Steps, Platforms	Alkyd	Gloss	Alkyd Floor, Porch & Trim Enamel**	None	70+@60°	400	2.2	55	70	1-3 Hrs.	24 Hrs.
			Tough Coat Heavy-Duty Alkyd High Gloss Enamel**	None	70+@60°	400	1.7	42	58	3-5 Hrs.	12 Hrs.
	Epoxy	Semi-Gloss	Tough Coat Polyamide Catalyzed Epoxy Semi-Gloss**	None	20-30@60°	185	5	56	70	1 Hr.	>6 Hrs. <30 Days
			Tough Coat Polyamide Catalyzed Epoxy Gloss**	None	80+@60°	185	4	56	70	1 Hr.	>6 Hrs. <30 Days
Concrete Walls, Unglazed Brick, Stucco	Latex	Flat	Platinum Latex Flat House Paint	T.P.S. Ext. Latex Primer or	0-5@85°	400	1.4	36	50	1 Hr.	4 Hrs.
			Great Life Latex Flat House Paint	Stretch Coat Acrylic	0-5@85°	400	1.3	32	46	1 Hr.	4 Hrs.
			ProLine Supreme Latex Flat House Paint	Masonry Primer	0-5@85°	400	1.5	38	55	1 Hr.	4 Hrs.
			ProLine Premium Latex Flat House Paint	(same)	0-5@85°	400	1.3	32	48	1 Hr.	4 Hrs.
			Stretch Coat Acrylic Elastomeric Topcoat	(same)	0-10@85°	73	3.7	45	59	4 Hrs.	24 Hrs.
			Platinum Latex Eggshell House Paint	(same)	10-20@60°	400	1.5	37	49	1 Hr.	4 Hrs.
	Latex	Eggshell	Great Life Latex Eggshell House Paint	(same)	10-20@60°	400	1.4	35	47	1 Hr.	4 Hrs.
			ProLine Supreme Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	35	46	1 Hr.	4 Hrs.
			ProLine Premium Latex Eggshell House Paint	(same)	10-20@60°	400	1.3	32	41	1 Hr.	4 Hrs.
			Platinum Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.4	36	48	1 Hr.	4 Hrs.
	Latex	Semi-Gloss	Great Life Latex Satin Gloss House Paint	(same)	35-45@60°	400	1.3	32	44	1 Hr.	4 Hrs.
			ProLine Supreme Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.3	33	44	1 Hr.	4 Hrs.
			ProLine Premium Latex Semi-Gloss House Paint	(same)	35-45@60°	400	1.2	29	40	1 Hr.	4 Hrs.
			Super Tough Coat DTM Acrylic Semi-Gloss Enamel**	(same)	30-40@60°	300	2.5	38	50	1 Hr.	4 Hrs.
			Tough Coat Acrylic Latex Semi-Gloss Industrial Enamel**	(same)	30-50@60°	395	1.5	36	48	30 Min.	4 Hrs.
			Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.
	Latex	Gloss	Super Tough Coat DTM Acrylic High Gloss Enamel**	(same)	70+@60°	300	2.5	37	46	1 Hr.	4 Hrs.
			Epoxy Semi-Gloss	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Semi-Gloss**	(same)	65+@60°	200-225	3	39	47	1 Hr.
	Epoxy	Gloss	Super Tough Coat Acrylic Water-Based Catalyzed Epoxy Gloss**	None	65+@60°	200-225	3	39	47	1 Hr.	18-24 Hrs.

**Appropriate for use in USDA inspected facilities for incidental, indirect contact, NOT direct food contact.

